

Distributed By: R.E. CARROLL, INC. 1570 NORTH OLDEN AVENUE TRENTON, NJ 08638-3204 USA PH: 609-695-6211/800-257-9365 www.recarroll.com

Specifications for

SUPER WHITE PROTOPET® Petrolatum Issued: 05/14/15

| PROPERTIES GUARANTEED | TEST METHOD | LIMITS |
|----------------------------------------|------------------------|-------------|
| Specific Gravity @ 60°C/25°C | LATM 128 | 0.815/0.880 |
| Residue On Ignition | USP (current revision) | 0.05 Max |
| Organic Acids | USP (current revision) | PASS |
| Alkalinity | USP (current revision) | PASS |
| Acidity | USP (current revision) | PASS |
| Fixed Oils, Fats, And Rosin | USP (current revision) | PASS |
| Color | USP (current revision) | PASS |
| Residual Solvents, Reportable Quantity | USP 467 | NONE |
| Lovibond Color, 3" CELL, Y | IP 17 | 1.0 Max. |
| Melting Point, °C | ASTM D127 | 54.4/60.0 |
| Consistency | ASTM D937 | 180/210 |
| Viscosity @ 210°F, SUS | ASTM D2161 | 60/75 |
| Sulfur Compounds | LATM 138 | PASS |
| Odor Rating, Panel Average | LATM 093 | 0.8 Max. |

SUPER WHITE PROTOPET[®] is a White Petrolatum USP meeting requirements for USP (current revision) and FDA requirements as per 21 CFR 172.880. It also meets the requirements of the Pharmacopeia of Japan.

053014216F

13722

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

Sonneborn, LLC 600 Parsippany Road Suite 100 Parsippany, NJ 07054 Technical Service 877.541.7144 Customer Service 877.948.2688 Fax 724.756.9386 www.sonneborn.com