



WEIFANG TIANRUI CHEMICAL CO., LTD

799 YIXIN STREET ECONOMIC AND TECHNIQUE DISTRICT WEIFANG SHANDONG CHINA
Phone:0086-536-7367777 Fax: 0086-536-736786 E-mail:jessicai@kitechem.com www.tianruichem.com

 **Kite** chlorinated polyethylene

Typical Physical Properties of Kite CM2500B For wire and cable products Applications

Physical Properties

	Values	Test Method
Chlorine content %	25 ± 3	GB/T7139
Heat of fusion J/g	≤ 2.0	Differential thermal method
Shore hardness shore A \leq	80	GB/T531
Tensile strength MPa \geq	8.0	GB/T528
Elongation at break % \geq	600	GB/T528
Mooney viscosity ML (1+4) 125°C	62 ± 9	GB/T1232
Volatile content % \leq	0.40	GB/T2914
Specific Gravity	1-1.5	

Packaging: 25kgs bags and bulk bags

DISTRIBUTED BY: R.E. CARROLL, INC.
1570 NORTH OLDEN AVENUE EXT., TRENTON, N.J. 08638-3204 USA
T: 609-695-6211/800-257-9365 F: 609-695-0102
www.recarroll.com