

# SUN-TACK

## Aromatic C9 Petroleum Resins

Distributed By: R.E. CARROLL INC. 1570 NORTH OLDEN AVE., TRENTON, N.J. 08638-3204 609-695-6211/800-257-9365

SUNTACK	SOFTENING POINT °C	SPEC. COLOR GARDNER#	TYPICAL COLOR GARDNER#	BROMINE NUMBER	ASH VALUE
U-90	100 ± 5	Max 6	4	< 30	Max 0.2%
U-101	110 ± 5	Max 6	4	< 30	Max 0.2%
U-120	120 ± 5	Max 6	4	< 30	Max 0.2%
U-120P	120 ± 5	Max 6	4	< 30	Max 0.2%
U-140	140 ± 5	Max 6	4	< 30	Max 0.2%
GS-90	100 ± 5	Max 8	6	< 30	Max 0.2%
SK-120	120 ± 5	Max 8	6	< 30	Max 0.2%
YT-130	130 ± 5	Max 8	6	< 30	Max 0.2%
YT-140	140 ± 5	Max 8	6	< 30	Max 0.2%
GA-100R	100 ± 5	Max 12	9	< 30	Max 0.2%
GA-120	120 ± 5	Max 12	9	< 30	Max 0.2%

### TEST METHODS

Softening Point ASTM E-28

Gardner Color ASTM D-1154 (50% in Toluene)

Bromine No. ASTM D-1158

Ash Value CNS-12777(WT%)

### PACKING

Granule form packed in 25Kg kraft paper bag or 500Kg jumbo bag

### APPLICATIONS

U-series : Adhesives, Hot Melt Adhesive, Pressure Sensitive Adhesive, Tape

SK-series : Paint & Varnish

GA-series : Rubber Compounding

YT-series : Printing Ink

Other : Color Asphalt Asphalt Modifier Plastic Modifier Sealant