

## AMBERYL MP - 35

PENTA MALEIC RESIN

DISTRIBUTED BY  
R. E. CARROLL, INC.  
1570 NORTH OLDEN AVENUE  
TRENTON, NJ 08638-3204  
609-695-6211 / 800-257-9265

**Amberyl resin MP-35** is made of gum rosin resin and corresponds to a maleic adduct esterified with pentaerythritol.

<b>Appearance</b>	<b>Glassy crystalline solid</b>
<b>Acid number</b>	<b>15 - 25</b>
<b>Softening Point (R &amp; B)</b>	<b>140 - 150</b>
<b>Color (50% xylene)</b>	<b>11 máx.</b>
<b>Viscosity of 60% xylene</b>	<b>V - X</b>

### FEATURES:

Soluble in aromatic solvents and ketones, slightly soluble in aliphatic solvents, and insoluble in alcohols and water.

Compatible with alkyd resins, drying oils and other rosin derivatives.

### APPLICATIONS:

Amberyl resin MP - 35 is recommended primarily for the formulation of coatings for lithography, as an additive modifier of hardness and drying air enamels and varnishes.

### STABILITY AND STORAGE

Handle with caution avoiding any spillage. Keep the bags closed. Store indoors without direct sunlight in a cool place free from moisture so that the product maintains its properties for the guaranteed time.

DO NOT REMOVE  
"Master Copy"

CONTROLLED COPY  
Valid Only If In Red