

PRODUCT DESCRIPTION

MAGOX[®] 98 HR is a finely sized, synthetic high-purity magnesium oxide produced from deep well brine. It is designed specifically for chemical processes where a rapid reaction rate and high purity is required.

CUSTOMER BENEFITS

MAGOX 98 HR delivers value through:

- Consistent product quality
- Vertically integrated manufacturing
- Being a domestically manufactured material

APPLICATIONS

- Wastewater neutralization
- Metal precipitation
- Silica removal
- Magnesium salt production
- Acid gas scrubbing
- Fertilizer production
- FCC additive catalyst production
- Oil drilling fluids
- Motor oil additive production

PACKAGING

MAGOX 98 HR is shipped in bulk, 25 kg bags and 1,000 kg super sacks.

DISTRIBUTED BY: R.E. CARROLL, INC. 1570 NORTH OLDEN AVENUE TRENTON NJ 08638-3204 T: 609-695-6211/800-257-9365 F: 609-695-0102 www.recarroll.com

Product manufactured in the USA

MAGOX[®] is a registered trademark of Premier Magnesia, LLC

Premier Magnesia, LLC, 300 Barr Harbor Drive, Suite 250, West Conshohocken, PA 19428 1-800-227-4287

http://www.premiermagnesia.com

Disclaimer: The information provided in this Product Data Sheet is correct to the best of our knowledge, information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, processing, storage, transportation, disposal and release and is not to be considered a warranty or quality specification. The information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process, unless specified in the text.

	Typical	<u>Max</u>	<u>Min</u>		
LOI (1000°C)	3.0	5.0			
MgO	98.2		97.0		
SiO ₂	0.35	0.5			
Fe ₂ O ₃	0.15	0.3			
AI_2O_3	0.10	0.2			
CaO	0.80	1.0			
Cl	0.30	0.5			
SO₃	0.05	0.3			
		(Ignited Oxide Basis)			

PHYSICAL PROPERTIES

	Typical	Max	<u>Min</u>	
S.S.A (m ² /g)	65	76	52	
Caustic Magnesia Reactivity (sec)	8			
Median Particle Size (micron)	5			
Bulk Density (Ib/ft ³)				
Loose	22			
Tapped	32			
Screen Analysis (wt.%)				
-100 Mesh			99.9	
-325 Mesh	99.5		99.0	

PRODUCT STORAGE

MAGOX 98 HR has a recommended shelf life of 12 months. The product is hygroscopic and exposure to external moisture may cause hardening. The product should be stored in an appropriate and dry location. Please contact Premier personnel with any questions.