

Technical Data Sheet

Distributed By: J.H. CALO CO., A DIVISION OF R.E. CARROLL INC.
1570 NORTH OLDEN AVENUE, EWING, N.J. 08638-3204
609-695-6211/800-257-9365 orders@recarroll.com



Cerita[®] Depilatory Wax 25-28B

Product type

Cerita[®] 25-28B is a high quality, wax based blend intended for depilatory applications. The material is formulated with natural waxes and resins and offers outstanding levels of performance when used correctly. It is pleasantly scented, has a (natural) dark amber color and is supplied in slab form.

Application

Cerita[®] 25-28B is applied as a film of warm, viscous liquid to the area of skin being treated. Before it sets completely, an optional strip of muslin or similar gauze may be pressed into the wax. A short while later, the solidified wax (or wax/fabric composite) is pulled smartly away from the skin, against the direction of hair growth, pulling out the hairs embedded in the wax layer.

Product Characteristics

| Technical Data | Typical | Method |
|-------------------------------------|----------|----------|
| Softening point (°F/°C) | 137 / 58 | PAK 0007 |
| Drop melting point (°F/°C) | 140 / 60 | PAK 0002 |
| Needle penetration 100g/ 77°F (dmm) | 8.5 | PAK 0004 |
| Specific gravity | 1.034 | PAK 0005 |
| Ash content (% w/w) | 0.0088 | PAK 0001 |

Handling Procedures

Melt and condition Cerita[®] 25-28B at 140 – 150°F / 60 – 65°C using a suitable temperature controlled vessel. Ideally, use a pot explicitly designed for depilatory waxing. Using a wooden spatula, or similar applicator, apply a thin film of the molten material to the area of skin to be treated, subsequently applying gauze if required. After waxing, residual material can be softened and removed with baby oil.

Take care to ensure the wax is at the correct temperature before skin application. Wax that is too hot can cause severe thermal burns.

When treating new subjects, apply material to a small test area first and watch for subsequent allergic reactions. Some people may be skin sensitive to the natural resins used in the formulation. **Do not continue with treatment if such a reaction occurs.** Please read and understand the relevant Safety Data Sheet (SDS) before using this material.

Disclaimer

Information and details given in this document, particularly any recommendations for application and use of our products are based on careful laboratory tests and prevailing practical experience and are believed to be correct at time of publication. The information is not binding, which is also generally true for our practical customer service, given verbally, in writing and by tests. Due to (possibly varying) conditions of transport, storage, process, substrate use or product application (which are beyond our knowledge and control), we strongly recommend to carry out sufficient tests in order to ensure that our products are suitable for the intended processes and applications. Further, it is the user's obligation to utilize this material with due care, in accordance with the information in the Safety Data Sheet (and with the information given in any other way by Paramelt) and in full compliance with health, safety and environmental regulations. Whilst proper care has been taken in the preparation of this document, no liability for damage or injury resulting from its use is accepted, other than the limited liability which may arise towards a contractual party on the basis of Paramelt's conditions of sale (a copy of these conditions is available on request). Paramelt's acceptance of any orders for this product is expressly conditional upon purchaser's assent to these conditions of sale. No information contained in this document (nor any information given verbally, in writing and by tests) is to be construed as permission, recommendation or inducement by Paramelt or its officers, employees or affiliates, to use any product or process so as to infringe upon or conflict with any patent. Paramelt does not attest or guarantee that the use of its products or processes will not infringe upon any patent; user is responsible for verifying its freedom to operate in any jurisdiction.