

DISTRIBUTED BY: R.E. CARROLL, INC. 1570 N. OLDEN AVE., TRENTON NJ 08638-3204 609-695-6211/800-257-9365 www.recarroll.com

Specifications for

BRITOL® 7T White Mineral Oil Tech Grade Issued: 9/12/2013

PROPERTIES GUARANTEED	TEST METHOD	LIMITS
Specific Gravity @ 25°C/25°C	ASTM D4052	0.835/0.862
Kin. Viscosity @ 40°C, mm ² /s	ASTM D445	10.8/13.6
Uv Absorbance	21CFR 178.3620(B)	PASS
Color, Saybolt	ASTM D156	20 Min.

TYPICAL PROPERTIES FOR BRITOL® 7T White Mineral Oil Tech Grade

PROPERTIES	TEST METHOD	TYPICAL VALUE
Pour Point ,°F	ASTM D97	-5
Wt. / Gal. @ 60°F	ASTM D4052	7.1

0317061012Z

18921

The Information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to Sonneborn's standard terms and conditions of sale, copies of which are available upon request and which are part of Sonneborn's invoices and/or order acknowledgments. Except as expressly provided in Sonneborn's standard terms and conditions of sale, no warranty, express or implied, including warranty of merchantability or fitness for particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.