



2780 Waterfront Parkway E Dr, Indianapolis, IN 46214.

Product Data Sheet

Product : CALSOL P910
Revised Date : 2018-08-16
Product Code : 300100010000

Test	UOM Description	Method Description	Min	Max	Typical
API GRAVITY @ 60°F		D4052			33.6
COLOR, ASTM		D1500		1	
VISCOSITY @ 40°C	cSt	D445			20.47
VISCOSITY @ 100°C	cSt	D445			4.08
VISCOSITY @ 100°F	SUS	D2161	100.0	115.0	107.4
VISCOSITY @ 210°F	SUS	D2161			39.9
VISCOSITY-GRAVITY CONSTANT		D2140			10.530
FLASH POINT, COC	°C	D92	193		208
FLASH POINT, COC	°F	D92	380		406
POUR POINT	°F	D97		5	5
POUR POINT	°C	D97		-15	-15
ANILINE POINT	°F	D611		228.0	218.8
ANILINE POINT	°C	D611		108.9	103.8
SATURATES	%(m)	D2007			92.5
REFRACTIVE INDEX @ 20°C		D1218			1.4700
UV ABSORPTIVITY, 260 NM		D2008			0.1
NEUTRALIZATION NUMBER	mg KOH/g	D974			0.013
VOLATILITY, 22HR/225°F	%(m)	D972			1.39

External Notes

**DISTRIBUTED BY: R.E. CARROLL, INC. 1570 NORTH OLDEN AVENUE EXT. TRENTON N.J. 08638 USA
T: 609-695-6211/800-257-9365 F: 609-695-0102 Orders@reccarroll.com**

Copyright 2012 Calumet Specialty Products Partners, L.P.

Calumet's sampling and testing procedures in effect at the time of production will be used for certification testing. Results may be based on tank certification, manufacturing data, periodic testing and/or most recent product restock. Results only represent the values one would expect if the product was tested in our laboratories with our test methods on the specified date. The typical values of product properties are not frequently measured and are not based on a statistically relevant number of tests. Calumet does not represent that the typical values contained on this data sheet represent the values in the product supplied to the user. The information in this document relates only to the named product. The user is solely responsible for determining the suitability of the product for its use intended by user, including use in any process and the combination of the product with any other material.