

## Product Information



# Corsol 1800

DISTRIBUTED BY: R.E. CARROLL, INC.  
1570 NORTH OLDEN AVENUE EXT.  
TRENTON N.J. 08638-3204 USA  
T: 609-695-6211/800-257-9365  
F: 609-695-0102 Orders@RECarroll.com  
www.recarroll.com

**DESCRIPTION** *Cross Corsol Series* are severely hydro treated naphthenic process oils manufactured from select crude streams. Corsol Series oil offer low pour point good solvency and color stability. They are ideal for production blending, adhesives, plastics and extended rubber.

| TEST NAME                        | TEST METHOD | SPECIFICATIONS |          |           |
|----------------------------------|-------------|----------------|----------|-----------|
|                                  |             | Minimum        | Maximum  | Typical   |
| Viscosity, cSt @ 40° C           | D-445       | 321.2          | 339      | 329.36    |
| Viscosity, cSt @ 100° C          | D-445       |                |          | 16.79     |
| Viscosity, SUS @ 100° F          | D-2161      | 1750           | 1850     | 1807      |
| Viscosity, SUS @ 210° F          | D-2161      |                |          | 87.6      |
| Gravity, API, 60° F              | D-4052      | 19.5           | 22.5     | 21.5      |
| Specific Gravity, 60/60° F       | D-1250      |                |          | 0.9248    |
| Pounds per Gallon @ 60° F        | D-1250      |                |          | 7.701     |
| Flash, COC, C° (F°)              | D-92        | 224 (435)      |          | 229 (445) |
| Pour Point, C° (°F)              | D-97        |                | -1 (+30) | -7 (+20)  |
| Color                            | D-1500      |                | 3.5      | L 3.0     |
| Aniline Point, C° (°F)           | D-611       |                |          | 95 (203)  |
| Viscosity-Gravity Constant       | D-2501      |                |          | 0.853     |
| Molecular Weight                 | D-2502      |                |          | 470       |
| Refractive Index @ 20° C         | D-1747      |                |          | 1.515     |
| Refractivity Intercept           | D-2159      |                |          | 1.053     |
| Aromatic Carbon Atoms, %Ca       | D-2140      |                |          | 20        |
| Naphthenic Carbon Atoms, %Cn     | D-2140      |                |          | 29        |
| Paraffinic Carbon Atoms, %Cp     | D-2140      |                |          | 51        |
| Asphaltenes, Mass %              | D-2007      |                |          | 0         |
| Polar Compounds, Mass %          | D-2007      |                |          | 2.5       |
| Aromatics, Mass %                | D-2007      |                |          | 40.5      |
| Saturates, Mass %                | D-2007      |                |          | 57.0      |
| Sulfur, Mass %                   | D-4294      |                |          | 0.10      |
| UV Absorptivity, 260 NM          | D-2008      |                |          | 7.2       |
| Volatility, 22 hr/225° F, % Mass | D-972       |                |          | 0.3       |
| DMSO Extract, wt.%               | IP-346      |                | 3.0      | < 3.0     |

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

**Health And Safety Information** See separate Material Safety Data Sheets available on request.

**CROSS OIL REFINING & MARKETING, INC.**

SMACKOVER, AR 71762 ■ USA ■ PHONE 800 864-6275 ■ [www.crossoil.com](http://www.crossoil.com)