

**DISTRIBUTED BY: J.H. CALO CO., A DIVISION OF R.E. CARROLL INC.**  
**1570 NORTH OLDEN AVENUE, EWING, N.J. 08638-3204**  
**609-695-6211/800-257-9365 www.recarroll.com**

## **Resinall 476**

**Resinall 476 is a rosin-modified maleic resin designed for use in alkyd type thermoplastic road marking compounds, road marking tape and nitrocellulose lacquer applications. With its low softening point, it can enhance flow and adhesion, while maintaining the other key compound properties.**

### **SPECIFICATIONS**

<b>Softening Point, R&amp;B, °C</b>	<b>100-110</b>
<b>Acid Number, mg KOH/g</b>	<b>30-45</b>
<b>Color, Gardner, Solid</b>	<b>8 max.</b>

### **TYPICAL PROPERTIES**

<b>Acetone Dilution on 60% Solids in Toluene cut, g/10g</b>	<b>&gt;200</b>
<b>Ethanol Dilution on 60% Solids in Toluene cut, g/10g</b>	<b>5</b>
<b>Mineral Spirits Dilution on 60% Solids in Toluene cut, g/10g</b>	<b>75</b>
<b>Pounds/Gallon, 25°C</b>	<b>9.2</b>
<b>Flash Point, COC, °C/°F</b>	<b>265/509</b>

**SOLUBLE in aromatic hydrocarbons, esters and ketones.**

**INSOLUBLE in mineral spirits, lower glycols and alcohol.**

**COMPATIBLE with nitrocellulose, ethyl cellulose, alkyds, plasticizers and most ingredients  
Commonly used in lacquer-type inks and coatings.**

**3-14-2006**

**mws**