

# *PRODUCT DATA*

## **Resinall 765**

**Resinall 765 is a very high softening point aliphatic hydrocarbon resin made from petroleum-derived monomers. It is chemically inert and possesses a high degree of unsaturation. Its uses include solvent-based coatings, paints, varnishes, printing inks, and as an aid for down hole drilling.**

### **SPECIFICATIONS**

<b>Softening Point, R&amp;B, °C</b>	<b>145-155</b>
<b>Viscosity, Gardner, 70% Solids in Toluene, 25°C, Letter, V7T</b>	<b>Z1-Z4</b>
<b>Color, Gardner, 70% Solids in Toluene, C7T</b>	<b>12 max.</b>

### **TYPICAL PROPERTIES**

<b>Viscosity, Gardner, 60% Solids in Mineral Spirits, Letter, V6MS</b>	<b>Z1</b>
<b>Color, Gardner, 60% Solids in Mineral Spirits, C6MS</b>	<b>10</b>
<b>Pounds/Gallon, 25°C</b>	<b>9.2</b>
<b>Flash Point, COC, °C/°F</b>	<b>238/460</b>

**SOLUBLE in aromatic, aliphatic and chlorinated hydrocarbons. Has limited solubility in low KB solvents.**

**INSOLUBLE in alcohols, acetone, glycols and water.**

**5-3-2006**

**mws**

**DISTRIBUTED BY: R.E. CARROLL, INC. 1570 NORTH OLDEN AVENUE EXT., EWING, N.J. 08638-3204 USA  
T: 609-695-6211/800-257-9365 F: 609-695-0102 [www.recarroll.com](http://www.recarroll.com)**

The information is based on experiments and data believed to be reliable. No warranty or guarantee is made as to accuracy or completeness. It is the users responsibility to determine the suitability and completeness of this information. Since application conditions are beyond our control, we can not guarantee results.

**RESINALL CORP. 3065 High Ridge Road, PO Box 8149, Stamford, CT 06903 203-329-7100**