



resinall®

Product Data

Distributed By: J.H. CALO CO., A DIVISION OF R.E. CARROLL INC.
1570 NORTH OLDEN AVENUE, TRENTON NJ 08638-3204 USA
TEL: 609-695-6211/800-257-9365 FAX: 609-695-0102 www.recarroll.com

Resinall 770

Resinall 770 is a hydrocarbon resin with good color and aliphatic solubility. It is generally suitable for tackifying solvent and waterborne adhesives based on SBS, SIS and SBR. Its use in hot melt applications is limited. Please consult with Resinall Technical Services before using it in any hot melt applications.

TYPICAL PROPERTIES ⁽¹⁾

Softening Point, R&B, °C	100
Color, Gardner, Solid Resin	5+
Color, Gardner, 50% Solids in Toluene	5-
Cloud Point in Odorless Mineral Spirits, °C	<-50
Cloud Point in MMAP ⁽²⁾ , °C	50
Cloud Point in DACP ⁽³⁾ , °C	52

Glass Transition Temperature, °C	43
----------------------------------	----

⁽¹⁾ Typical values are not specifications. They are provided to help in formulating decisions.

⁽²⁾ 1:2 mixture of methylcyclohexane and aniline

⁽³⁾ 1:1 mixture of xylene and 4-hydroxy-4-methyl-2-pentone

mws

5-2-2007

This information is based on experiments and data believed to be reliable. No warranty or guarantee is made as to accuracy or completeness. It is the users responsibility to determine the suitability and completeness of this information for his particular use. Since application conditions are beyond our control, we can not guarantee results.