



WEIFANG TIANRUI CHEMICAL CO., LTD

799 YIXIN STREET ECONOMIC AND TECHNIQUE DISTRICT WEIFANG SHANDONG CHINA
Phone:0086-536-7367777 Fax: 0086-536-736786 E-mail:tianrui@tianruichem.com www.tianruichem.com

 **Kite** chlorinated polyethylene

Distributed By: R.E. CARROLL, INC.
1570 NORTH OLDEN AVENUE
TRENTON, NJ 08638-3204 USA
T: 609-695-6211/800-257-9365
F: 609-695-0102 www.recarroll.com

Typical Physical Properties of Kite CM 6605 For Elastomers Applications

Physical Properties

	Values	Test Method
Chlorine content %	35 ± 1	GB/T7139
Heat of fusion J/g	≤ 1.0	Differential thermal method
Shore hardness shore A $\leq$	60	GB/T531
Tensile strength MPa $\geq$	8.0	GB/T528
Elongation at break % $\geq$	800	GB/T528
Mooney viscosity ML (1+4) 125°C (1+4) 125°C	81-85	GB/T1232
Volatile content % $\leq$	0.40	GB/T2914

Packaging: 25kgs bags and bulk bags