



R.E. Carroll, Inc.

Raw Materials • Fillers • Petroleum Products

1570 NORTH OLDEN AVENUE • TRENTON, NEW JERSEY 08638-3204

609/695-6211 • 800-257-9365 • FAX 609/695-0102

www.recarroll.com

PRODUCT SPECIFICATION

KEP-350

Test Description	Method	Typical	Min.	Max.
Volatile Content, wt%	D1416			0.75
Ethylene Content, wt%	D3900-95		53.0	60.0
ENB Content, wt%	D6047		7.0	8.3
Raw Rubber Mooney Viscosity	D1646-95		46.0	54.0
ML (1+4)@125C) MU				
Data taken from COA dated 2/16/16				