



R. E. Carroll, Inc.

Raw Materials • Fillers • Petroleum Products



RECCO 186A-MICRO

PRODUCT DATA

Properties

Congeaing Point	(ASTM D-938)	78.3-83.0 °C 173-181 °F
Drop Melting Point	(ASTM D-127)	82-87 °C 180-188.6 °F
Viscosity @ 100C	(ASTM D-445)	18-23 cSt
Penetration @ 25C	(ASTM D-1321)	15-20 dmm
Color	(ASTM D-1500)	2 Max
FDA	Complies 172.866 & 178.3710	

The information contained herein is, to the best of our knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability of fitness for purpose of the product or products described herein. In submitting this information, no liability is assumed or license or other rights express or implied given with respect to any existing or pending patent, patent applications or trademarks. The observance of all legal regulations and patents is the responsibility of the user.

April 08, 1998